

# TECHNICAL DATA SHEET

**PRODUCT CODE(S):**

Q-0960

**PRODUCT DESCRIPTION:**

WHITSLIK 15 INSIDE TIRE LUBE

**PHYSICAL PROPERTIES:**

COLOR:	WHITE
TYPE:	WATER-BASED
VISCOSITY:	600-1,000 CPS #2@12
WEIGHT PER GALLON:	8.31 lbs/gal ± 0.30 lbs. 1.00 g/ml ± 0.04 g/ml
SPECIFIC GRAVITY (ASTM D 1475-90):	0.997 ± 0.35
GLOSS @ 60°:	N/A
pH:	N/A
FLASH POINT:	> 212 °F 100.0 °C
SOLIDS:	15.84 % by weight 15.97 % by volume
THEORETICAL COVERAGE:	256.16 ft <sup>2</sup> / gal @ 1.0 mil dry 6.29 m <sup>2</sup> /l @ 25.4 μ
VOC:	0.34 lb(s)/gal ( 40.8 g/l)
VOC (U.S.):	0.34 lb(s)/gal ( 40.8 g/l)

**APPLICATION:**

METHOD:	SPRAY
CURE METHOD:	
REDUCTION:	USE AS SUPPLIED
CLEAN UP:	WATER
RECOMMENDED EQUIPMENT:	

**SUBSTRATE:**

TYPE:	UNCURED RUBBER COMPOUNDS
PREPARATION:	NONE

**HANDLING & STORAGE:**

SHELF LIFE:	6 MONTHS
FREEZE CAUTION:	PROTECT FROM FREEZING
RECOMMENDED STORAGE:	COOL, DRY LOCATION

**ADDITIONAL GUIDELINES:**

MIX WELL BEFORE USING. PRODUCT TURNS CLEAR UPON CURING.  
DOES NOT CONTAIN MICA OR ANY HAZARDOUS AIR POLLUTANTS (HAPS).

## A focused partner in advanced coating, chemical & manufacturing solutions...

Founded in 1878, APV Engineered Coatings custom engineers and manufactures industrial coatings and advanced chemical products out its state-of-the-art facility in Akron, Ohio. APV is a partner for some of the world's top producing manufacturers due to our expertise in chemical composition, the commercialization of advanced materials, and large-scale production with acute quality control. Our innovative solutions have been integrated into a variety of industries for unique applications.

At APV, clients work with knowledgeable and personable staff who are focused on delivering optimum solutions in an unprecedented timeframe. APV thrives by recognizing the importance of our clients' success, which have proved to create long-standing partnerships.



APV Engineered Coatings, Inc.  
1390 Firestone Parkway  
Akron, Ohio 44301 USA  
800.772.3452  
sales@apvcoatings.com  
www.apvcoatings.com

rev. date: 09/12/2019

The information and data given herein are based upon tests and reports considered reliable and are believed to be accurate. However, due to varied application and handling methods, no guarantee of duplicate performance, expressed or implied, is made.