

TECHNICAL DATA SHEET

**PRODUCT CODE(S):**

P-6922

PRODUCT DESCRIPTION:

W/B WSW PROTECTIVE COATING

PHYSICAL PROPERTIES:

COLOR:	BLUE
TYPE:	WATER BASED
VISCOSITY:	600 +/- 200 LVF #2 @ 12 RPM
WEIGHT PER GALLON:	9.27 lbs/gal ± 0.30 lbs. 1.11 g/ml ± 0.04 g/ml
SPECIFIC GRAVITY (ASTM D 1475-90):	1.110 ± 0.04
GLOSS @ 60°:	N/A
pH:	6.0-8.0
FLASH POINT:	> 200 °F 93.3 °C
SOLIDS:	29.9 % by weight 23.64 % by volume
THEORETICAL COVERAGE:	379.19 ft ² / gal @ 1.0 mil dry 9.30 m ² /l @ 25.4 μ
VOC:	0.09 lb(s)/gal (10.8 g/l)
VOC (U.S.):	0.09 lb(s)/gal (10.8 g/l)

APPLICATION:

METHOD:	SPRAY
CURE METHOD:	AIR DRY 4-7 MIN. OVER WARM TIRES
REDUCTION:	NONE RECOMMENDED
CLEAN UP:	L-400 SOLVENT
RECOMMENDED EQUIPMENT:	

SUBSTRATE:

TYPE:	TIRE SIDEWALL
PREPARATION:	CLEAN, DRY, FREE FROM CONTAMINANTS

HANDLING & STORAGE:

SHELF LIFE:	1 YEAR
FREEZE CAUTION:	Protect from freezing
RECOMMENDED STORAGE:	COOL, DRY LOCATION

ADDITIONAL GUIDELINES:

MIX WELL BEFORE USING, BEING CAREFUL NOT TO GENERATE FOAM. CLOSE CONTAINER AFTER USE. THIS PRODUCT IS FREE FROM HAZARDOUS AIR POLLUTANTS (HAPS).

A focused partner in advanced coating, chemical & manufacturing solutions...

Founded in 1878, APV Engineered Coatings custom engineers and manufactures industrial coatings and advanced chemical products out its state-of-the-art facility in Akron, Ohio. APV is a partner for some of the world's top producing manufacturers due to our expertise in chemical composition, the commercialization of advanced materials, and large-scale production with acute quality control. Our innovative solutions have been integrated into a variety of industries for unique applications.

At APV, clients work with knowledgeable and personable staff who are focused on delivering optimum solutions in an unprecedented timeframe. APV thrives by recognizing the importance of our clients' success, which have proved to create long-standing partnerships.



APV Engineered Coatings, Inc.
1390 Firestone Parkway
Akron, Ohio 44301 USA
800.772.3452
sales@apvcoatings.com
www.apvcoatings.com

rev. date: 06/04/2019

The information and data given herein are based upon tests and reports considered reliable and are believed to be accurate. However, due to varied application and handling methods, no guarantee of duplicate performance, expressed or implied, is made.