

| THE COATINGS SYSTEMS | NEVERFADE® ORIGINAL BASE | NEVERFADE® METAL BASE | BR-W1500 UNIVERSAL PRIMER | BR-W1650 BONDING PRIMER |
|--------------------------------------|--|--|---|--|
| TYPE | WATER-BASED | WATER-BASED | WATER-BASED | WATER-BASED |
| MIX | ONE COMPONENT | ONE COMPONENT | ONE COMPONENT | ONE COMPONENT |
| REDUCTION | MAX 1 - 4 CUPS 8 FL OZ - 38.4 FL OZ | MAX 1 - 4 CUPS 8 FL OZ - 38.4 FL OZ | MAX 2-3 TABLESPOONS, 2 FL OZ - 8 FL OZ | MAX 2-3 TABLESPOONS, 2 FL OZ - 8 FL OZ |
| VISCOSITY TARGET | 63 SECONDS, #3 ZAHN CUP | 63 SECONDS, #3 ZAHN CUP | 55 SECONDS, #3 ZAHN CUP | 54 SECONDS, #3 ZAHN CUP |
| EQUIPMENT | HVLP, AIRLESS, AIR ASSISTED, BRUSH OR ROLL | HVLP, AIRLESS, AIR ASSISTED, BRUSH OR ROLL | HVLP, AIRLESS, AIR ASSISTED, BRUSH OR ROLL | HVLP, AIRLESS, AIR ASSISTED, BRUSH OR ROLL |
| FILM THICKNESS | 5-6 MILS WET 2 MILS DRY | 5-6 MILS WET 2 MILS DRY | 3 MILS WET 1 MIL DRY | 3 MILS WET 1 MIL DRY |
| COVERAGE ESTIMATE | 250-300 SQ FT/GAL | 350-400 SQ FT/GAL | 400-450 SQ FT/GAL | 400-450 SQ FT/GAL |
| DRY TO TOUCH | 15 MINUTES | 15 MINUTES | 15 MINUTES | 15 MINUTES |
| RECOMMENDED RECOAT WINDOW | MIN 3 HRS MAX 48 HRS (Same product) | MIN 3 HRS MAX 48 HRS (Same product) | MIN 24 HRS MAX 7 DAYS | MIN 24 HRS MAX 7 DAYS |
| FULLY CURED | 30 DAYS | 30 DAYS | 7 DAYS | 7 DAYS |
| APPLICATION TEMPERATURE RANGE | 55° F – 85° F | 55° F – 85° F | 55° F – 85° F | 55° F – 85° F |
| HUMIDITY | 5° F ABOVE DEW POINT | 5° F ABOVE DEW POINT | 5° F ABOVE DEW POINT | 5° F ABOVE DEW POINT |
| ADHESION TO SUBSTRATES | PRIMER REQUIRED ADHESION: ASTM D3359 | PRIMER REQUIRED ADHESION: ASTM D3359 | STUCCO, EIFS, VINYL, MASONRY, CONCRETE, FIBER CEMENT, WOOD ADHESION: ASTM D3359 | PLASTICS, FERROUS & NON-FERROUS METALS, COATED SURFACES INCLUDING: SILICONIZED POLYESTER, KYNAR 500®, FEVE COATINGS, AND POWDER COATINGS ADHESION: ASTM D3359 |

For technical assistance contact ppcprotectivecoatings@pittsburghpaints.com

